

FLAMMABILITY TEST REPORT

Report No.: LEI20061078A **Date Received:** 15/06/20 **Date Tested:** 19/06/20 **Date Issued:** 19/06/20

Company Name & Address: VITAFOAM HUNGARY LTD.
H-7030 PAKS, HRSZ 8806/2
7030

Contact Name: MARIANN LACZA

Sample Details

Order No.: 3
Description: CH3728
Ref. / Style No.: Not stated
Colour: Green
Quality: Combustion modified high resilience polyurethane foam made with polyol, TDI and flame retardant (raw or coloured) Density: 37kg/m³ Hardness: 112N
Supplier: Not stated
Batch No.: P831(production date: 2020.03.03.)
Intended Use: Not stated
Number of Samples: 4 pieces (sample cutting date: 2020.06.05)
Quoted Fibre Composition: Not stated
Retailer: Not stated
Specification No.: Not stated
Sample Description: Green coloured polyurethane foam

Test Method	Pre Treatment	Flammability Performance Requirements	Result
BS 5852: Part 2: 1982, Ignition source 5 (Crib 5) as modified by Schedule 1 Part 1 of the Furniture & Furnishings (Fire) (Safety) Regulations 1988 (As Amended).	None	As Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	Complies



.....
STEVEN OWEN
(Technical & Operational Excellence Manager)

.....
ANDREW HALLETT
(Flammability Team Leader)

.....
CAROLE SPOWART
(Flammability Administrator)

.....
GREGORY JAMES
(Flammability Technician)

FLAMMABILITY TEST REPORT

Filling Specification

Filling Type: Polyurethane Foam
Density / Hardness: Not stated / Not stated
Cover Fabric: Standard test fabric as detailed in Schedule 1 Part 1 of The Furniture (Fire) (Safety) Regulations 1988 (as amended).

Uncertainty of Measurement

The uncertainty of measurement has been estimated to be 5.99%

Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of $20\pm 5^{\circ}\text{C}$ and a relative humidity of $50\pm 20\%$
At Time of Testing: Temperature between 15°C & 30°C . Relative humidity between 20% & 70%

Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the fully potential fire hazard of the materials in use."

Pass / Fail Criteria	Initial test		Repeat test	
Progressive smouldering failure				
Externally detectable amounts of smoke, heat or glowing 60 min after crib ignition	No		No	
Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Smouldering essentially consumed the test specimen within the duration of the test	No		No	
Flaming failure				
The test specimen continued to flame for more than 10 minutes after the ignition of the crib	No		No	
Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction	No		No	
Flaming essentially consumed the test specimen within the duration of the test	No		No	
Final examination				
Progressive smouldering was observed when the sample was dismantled	No		No	
Comments				
Time to extinction of flames after crib ignition	4 Minutes 15 Seconds		3 Minutes 55 Seconds	
Time to extinction of glowing after crib ignition	Due to the position of the crib within the test specimen it was not possible to see when glowing ceased		Due to the position of the crib within the test specimen it was not possible to see when glowing ceased	
Time to extinction of smoke after crib ignition	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased		Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased	
Maximum extent of damage to back (mm) Length / Width	400	145	400	160
Maximum extent of damage to base (mm) Length / Width	125	180	130	205
188T197he resultant mass loss exceeded 60g	No (36g)		No (34g)	
Test Result	PASS		PASS	

Conclusions

The sample tested meets the requirements of Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

FLAMMABILITY TEST REPORT

The client acknowledges and agrees that any services provided and/or reports produced by Intertek are done so within the limits of the scope of work agreed pursuant to the client's specific instructions. This report relates specifically to the sample(s) tested that were drawn and delivered by the client or their nominated third party. Intertek does not make any representation or warranty for any bulk samples or certify the bulk samples received from the client. Furthermore, Intertek does not provide a warranty or verification on the sample(s) representing any specific goods, material and/or shipment and only relate to the sample(s) as received and tested. Intertek have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. In no event, will the contents of any reports or any extracts, excerpts or parts of any reports be distributed or published without the prior written consent of Intertek in each instance. Only the client is authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Unless otherwise specified all compliance and pass/fail statements are binary simple acceptance based on the tolerance interval and, with the exception of graded methods, a test uncertainty ratio greater (TUR) than 4:1. For graded methods the TUR will drop to as low as 0.5:1 when the tolerance limits are within a grade division of the upper scale limit. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are on or close to Specification Limits / Requirements and in such cases it should be noted that the risk of false acceptance or rejection may be as high as 50%, for further information please refer to ILAC G8.